Amendments to the Claims:

This listing of the claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (**Currently Amended**) Resin-coated metal ~~plates~~ plate for a drawn can, ~~comprised of metal plates~~ comprises:

a metal plate and a resin film ~~that is~~being applied to ~~the~~ at least one surface ~~side or to both sides~~ of the metal plate, wherein the resin film comprises;~~is comprised of two layers [of],~~

~~[A]~~ a crystallized saturated polyester resin layer [A] that is ~~induced~~ produced from dicarboxylic acid and ~~dithydroxy~~ dihydroxy compounds ~~and~~, ~~within~~ the components of dicarboxylic acid are terephthalic acid and isophthalic acid, or only terephthalic acid[,]; and

~~[B]~~ a layer composed of resin [B] that is comprised of saturated polyester resin (i) and ionomer resin (ii),

wherein the layer composed of resin ~~[B]~~ [B] is laminated on the metal plate to tightly contact with [it] the metal plate, and

on a surface of the crystallized saturated polyester resin layer [A] is a highly crystallized layer (X) formed by a heat treatment of ~~on the polar surface of the crystallized saturated polyester resin layer [A]~~ the resin-coated metal plate;

wherein the highly crystallized layer (X) is at least 2% of thickness of the crystallized saturated polyester resin layer [A] ~~[A], a highly crystallized layer (X) is formed~~.

2. (**Currently Amended**) Resin-coated metal plates according to claim 1, wherein a degree of crystallization of the highly crystallized layer (X) is 10-60%.

3. (**Original**) Drawn cans formed by drawing or re-drawing of the resin-coated metal plates according to claim 1, to have the highly crystallized layer (X) become the inner surface side of the can.

4. (**Original**) Drawn cans formed by drawing or re-drawing of the resin-coated metal plates according to claim 2, to have the highly crystallized layer (X) become the inner surface side of the can.